

**MONARFLEX® Netofol 200 VB****Product Description:**

Product name	<b>MONARFLEX® Netofol 200 VB</b>
Thickness (mm) (prEN 1849-2)	0,20 mm
Mass/sqr (g/m <sup>2</sup> ) (prEN 1849-2)	200 g/m <sup>2</sup>
Roll size (prEN 1848-2)	2,00 x 50 m
Description	3 layer product: <ul style="list-style-type: none"><li>• 2 layers of LDPE</li><li>• 1 layer of reinforcing HPDE 12 x 12 mm net – Ø0,38 mm</li></ul>
Temperature stability	-40 °C to +80 °C

(MD: Machine Direction) (TD: Transverse Direction)		<b>MONARFLEX® Netofol 200 VB</b>	
		MD	TD
Tensile Strength (prEN 12311-2:2000)	Maximum force (N/5 cm)	295	245
	Elongation at max force in %	22	23
Nail Tear Resistance (prEN 12310-1)	Maximum force (N)	250	235

**Mechanical Properties:****Water Vapour Transmission:**

	<b>MONARFLEX® Netofol 200 VB</b>
According to (EN ISO 12572 condition C)	0,3 g/m <sup>2</sup> - 24 hours

**Water tightness:**

	<b>MONARFLEX® Netofol 200 VB</b>
According to (prEN 1928:2000)	Pass